

TREND

PREVODOVÝ SYSTÉM ZDVIHU VYLOŽNIKU KU 800					Převodový olej: PP 80W90								
Číslo vzorku	Datum	Viskozita při 40 °C, mm ² /s	Obsah vody - FTIR	Oxidace (Abs/cm)	Obsah Sn (mg/kg)	Obsah Ni (mg/kg)	Obsah Pb (mg/kg)	Obsah Cr (mg/kg)	Obsah Cu (mg/kg)	Obsah Fe (mg/kg)	Obsah K (mg/kg)	Obsah Si (mg/kg)	Obsah Zn (mg/kg)
6322542	31.1.2009	117,5	<0,1	11	<1	2	2	2	19	206	5	15	253
6322651	6.11.2019	119	<0,1	2	<1	2	2	1	18	153	3	9	265
6323389	23.6.2011	130	<0,1	<1,0	<1	<1	1	1	4	84	1	7	76
6323385	12.12.2012	122	<0,1	<1,0	<1	<1	<1	<1	8	60	<1	4	77
8139164	12.5.2014	126	<0,1	<1,0	1	<1	<1	<1	7	27	1	4	64

